# Roof and Plinth Paint

Technical information sheet




5l / Item number 095005001 / EAN 4007955950059 (Schiefer)
5l / Item number 095205001 / EAN 4007955952053 (Torf)
5l / Item number 095305001 / EAN 4007955953050 (Havanna)
5l / Item number 095405001 / EAN 4007955954057 (Sandstein)
5l / Item number 095505001 / EAN 4007955955054 (Steingrau)
5l / Item number 095705001 / EAN 4007955957058 (Ziegelrot)
5l / Item number 096005001 / EAN 4007955960058 (Terra)
5l / Item number 096105001 / EAN 4007955961055 (Basaltblau)
5l / Item number 096205001 / EAN 4007955962052 (Betongrau)
5l / Item number 096305001 / EAN 4007955963059 (Anthrazit)

Highly opaque and very economical synthetic dispersion paint for long-lasting, lightfast coatings. Suitable for render, masonry, fibre cement roofs, roof tiles and sound old coatings. The paint impresses with its even flow, good adhesion and high weather resistance. Ideal for indoor and outdoor use and perfect for permanently well-maintained, colour-stable surfaces.

- Wet abrasion resistance class 2 according to DIN EN 13300
- abrasion-resistant
- Weatherproof
- Solvent-free and breathable
- water-dilutable
- Can be mixed with each other and with white façade paint
- for indoors and outdoors

## Area of application

Suitable for coating roof tiles, fibre cement roofs (e.g. Eternit), render, concrete, masonry and similar mineral substrates.

## Preparation

The substrate must be dry, clean, stable and free of dust and grease. If necessary, clean the surface. Use as roof paint: Pre-treat the surface with a quality deep penetrating primer. Only apply the roof and skirting paint once the primer is completely dry (12 - 24 hours depending on the ambient temperature and humidity). Use as skirting paint: An important prerequisite for the durability of the paint is that the skirting is protected against moisture from the ground. Prime highly absorbent and sanding substrates with a quality primer.

## Processing

Stir the paint well before use and apply with a roller, brush or using the airless method. The paint can be thinned with approx. 5 % water for the base coat. After the first coat has dried, apply the paint once or twice undiluted as required.

## Consumption

1 litre is sufficient for approx. 6 m² with a single coat - depending on the absorbency and structure of the substrate.

## Storage

Keep container tightly closed and store in a cool but frost-free place.

## Notes

For larger areas, ensure that the batches are identical. Mix different batches together. Do not apply below + 5 °C substrate and room temperature. Clean tools with water immediately after use. Only dispose of empty containers for recycling. EU VOC limit value for this product: (Cat.: A/c, Wb) = 40 g/l (2010). VOC content of this product max.: 1 g/l.



Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

**Note:**
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.