

Protective paint

Technical information sheet

750ml / Item no.020319 / EAN 4016215020319

2,5l / Item no.020326 / EAN 4016215020326

5l / Item no.020357 / EAN 4016215020357

10l / Item no.020401 / EAN 4016215020401



Highly opaque, white protective paint with integrated long-term film protection that reliably protects against fungal and mould infestation indoors. Ideal for kitchens, bathrooms and other damp rooms. The paint impresses with its high opacity, scrub-resistant surface and an even, matt finish. Easy to apply to mineral substrates, wallpaper and woodchip and ensures permanently clean, hygienic and well-maintained wall surfaces.

- with film preservation for long-term protection of the paint film against mould infestation
- Ideal for kitchens, bathrooms and wet rooms
- High opacity
- abrasion-resistant
- Contrast ratio class 2 with a yield of 6 m²/l
- Wet abrasion resistance class 2 according to DIN EN 13300
- for indoors

Area of application

White special paint with high covering power and film protection against mould. For interior wall and ceiling surfaces, ideal for bathrooms and kitchens.

Preparation

For substrates such as concrete, masonry, levelling compounds, cement, gypsum and lime plaster, plasterboard and other drywall, firmly adhering emulsion paint coats as well as woodchip, glass fabric and other paintable wallpaper and wall coverings. Ceiling panels made of polystyrene and similar surfaces. The substrate must be dry, clean, sound and free of dust and grease. Remove loose material, old wallpaper and poorly adhering paints from the substrate. Prime highly absorbent, sanding and chalking substrates with baufan Deep Primer LF. Repair cracks, holes and unevenness with a suitable baufan levelling compound. Surfaces already infested with mould must be cleaned with baufan Mould Remover before applying the first coat.

Processing

Stir well before use and apply with a roller, brush, paintbrush, flat brush or suitable spraying equipment. Two coats are necessary for optimum film protection. As a primer, the paint can be diluted with max. 10 % water. After the first coat has dried through, the final coat should be applied undiluted. When coating larger areas, work wet-on-wet to avoid build-up. Can be tinted with up to 5 % full colour and tinting paint or max. 0.2 % universal tinting concentrate. Clean tools with water immediately after use. Notes on airless spray application: Spray angle: 50° Nozzle: 0.023 - 0.027 Spray pressure: 120 - 180 bar Drying time: approx. 6 - 8 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); longer drying time under unfavourable conditions.

Consumption

Smooth surfaces/fine plaster grain → from 150 ml/m² Determine exact consumption quantity by test coating on the object.

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least until: see batch label.

Notes

Processing temperature: Not below +5 °C for material, circulating air and substrate Do not cover surfaces to be painted. Keep out of reach of children. Ensure adequate ventilation during application and drying. Do not inhale spray mist. Avoid eating, drinking and smoking while using the paint. caution! Hazardous respirable droplets may be produced when spraying.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

Do not inhale aerosol or mist. Use combination filter A2/P2 when spraying. For safety-relevant data, please refer to the safety data sheet. Current safety data sheets are available on our website www.baufan.de or at info@baufan.de.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.