

Interior Filler

Technical information sheet

500g / Item no.101209 / EAN 4016215101209
1kg / Item no.101261 / EAN 4016215101261
5kg / Item no.101247 / EAN 4016215101247
10kg / Item no.101285 / EAN 4016215101285
20kg / Item no.101254 / EAN 4016215101254



A gypsum-based, cellulose-reinforced filler for interior walls and ceilings. Ideally suited for filling cracks and holes, smoothing uneven surfaces, anchoring wall plugs, jointing plasterboard and modelling.

- for filling, smoothing and modelling
- smooth, gypsum-based filler
- with methyl cellulose for optimum adhesion
- Easy and safe to process
- Processing time: 60 minutes
- hardens without cracking
- provides an ideal base for paint, wallpaper and the like.

Area of application

A smooth, gypsum-based interior filler for walls and ceilings.

Preparation

For all mineral substrates (concrete, gypsum, lime and cement render, masonry, etc.) as well as plasterboard and gypsum fibre boards. Not suitable for glass, metal, plastic or wood. For interior surfaces exposed to moisture and for outdoor use, we recommend baufan Exterior Filler.

The substrate must be dry, sound, and free from dust and grease. Remove any loose particles. Pre-treat very smooth concrete and highly absorbent, sandy or chalky substrates with baufan Tiefgrund LF.

Processing

Add 2 parts baufan Interior Filler to 1 part clean, cold water and stir until a paste-like, lump-free mixture is formed (mixing ratio: 1 kg baufan Interior Filler – approx. 600 ml water). Leave the mixture to stand for approx. three minutes, then stir again. The prepared filler remains workable for approx. 1 hour and must not be diluted at a later stage.

Apply baufan Interior Filler with a filler knife or trowel and smooth it off until flush with the surface. The filler is easy to smooth and can be sanded down if necessary once it is completely dry. To ensure a uniform level of absorbency across the surface during touch-up work, it is recommended that, once thoroughly dry, the filled areas – or indeed the entire surface – be treated once more with baufan Tiefgrund LF.

Consumption

approx. 1 kg of powder per m² at an application thickness of 1 mm

Storage

Keep containers tightly closed and store in a cool, dry place.

Notes

Keep out of the reach of children. Do not apply when the object or ambient temperature is below +5 °C. Clean tools with water after use.

Before use, refer to the safety information in the safety data sheet. Up-to-date safety data sheets are available on our

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

website at www.baufan.de.

Only send completely empty containers for recycling. Cured material residues can be disposed of as household waste or as construction site waste (waste code no. EWC 17 08 02).

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.