

Lime Coating

Technical information sheet

2,5l / Item no.100011 / EAN 4016215100011

5l / Item no.100028 / EAN 4016215100028

10l / Item no.100035 / EAN 4016215100035



A mineral-based paint made from white hydrated lime. Forms a wipe-resistant surface once dry. Suitable for damp rooms, utility rooms, garages, cellars, wine cellars, stables and similar areas. Can also be used outdoors on mineral substrates protected from driving rain. Ideal for listed buildings. Characterised by a high degree of whiteness and excellent breathability.

- mineral-based paint made from hydrated white lime
- ready for use
- Ideal for damp rooms, laundry rooms, garages, cellars, etc.
- High degree of whiteness
- smudge-proof
- Highly water vapour permeable
- Free from preservatives, solvents and plasticisers

Area of application

Mineral-based lime wash made from hydrated white lime, for interior and exterior surfaces. Smudge-resistant, breathable, and ideal for damp rooms and heritage conservation projects.

Preparation

For all mineral substrates such as lime- and cement-based plasters and coatings. The substrate must be alkali-resistant, dry, clean, sound, and free from dust and grease. Remove loose material, old wallpaper and poorly adhering coatings from the substrate. Pre-treat highly absorbent, sandy and chalky substrates with bausfan Silicate Fixative. If in doubt, carry out a test coat. Repair cracks, holes and uneven areas with a suitable bausfan filler.

Processing

Stir well before use and apply with a roller, brush, paintbrush, flat brush or suitable spray equipment. If required, the paint may be diluted with up to 15 per cent water for a primer coat; apply undiluted as a top coat. Clean tools with clean water immediately after use.

Drying time:

approx. 5 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); drying time will be correspondingly longer under unfavourable conditions.

Tinting:

For interior use, the paint can be tinted with up to 4% universal tinting concentrates (LW Oxyd types). Do not tint for exterior use.

Notes on airless spray application:

The lime wash must first be sieved without pressure (mesh size 0.5 mm).

Machine filter: 30 mesh

Spray angle: 40°-50°

Nozzle: 0.025-0.027

Spray pressure: 120-180 bar

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

Consumption

Smooth surfaces/fine-grained plaster → from 150 ml/m²

Determine the exact amount required by carrying out a test application on the surface.

Storage

Store the container tightly sealed in a cool place, but away from frost.

Notes

Application temperature:

+5 °C to +30 °C for the material, ambient air and substrate.

Before use, refer to the safety information in the safety data sheet. Up-to-date safety data sheets are available on our website at www.baufan.de.

Keep out of the reach of children. Cover surfaces not to be painted (glass, wood, etc.) and protect them from splashes. Ensure adequate ventilation during application and drying. When spraying, use an A2/P2 combination filter. Avoid eating, drinking and smoking whilst using the paint. Do not allow the product to enter the sewerage system, watercourses or the ground.

When used outdoors, the durability of the coating depends heavily on weather conditions. The lime wash can be modified with synthetic resin by adding baufan latex binder. This improves its scrub resistance and weather resistance. Do not mix with other paints.

baufan lime paint can be easily recoated with the same material. Before applying other types of coating, the lime paint should always be washed off or brushed away.

Disposal:

Only send completely empty containers for recycling. Dried-out material residues can be disposed of as household waste or as construction site waste. Dispose of liquid residues in accordance with EWC waste code No. 08 01 12.

GISCODE for coating materials: BSW60

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.