

Latex Paint Pure White

Technical information sheet

750ml / Item no.100202 / EAN 4016215100202

2,5l / Item no.100226 / EAN 4016215100226

5l / Item no.100240 / EAN 4016215100240

10l / Item no.100264 / EAN 4016215100264



An abrasion-resistant, highly opaque emulsion paint for interior and exterior use. Provides excellent protection and long-lasting colour on a wide range of substrates. It is weather-resistant, easy to apply and provides an even, matt finish. Ideal for walls and ceilings in living and outdoor areas subject to heavy use.

- Wet abrasion resistance R class 2 according to DIN EN 13300
- Contrast ratio H₁₀ class 3 with a yield of 6.5 m²/l
- for hard-wearing coatings
- white opaque
- gloss level matt
- Free from solvents, plasticisers and fogging-active substances
- airless sprayable

Area of application

Emulsion paint for interior and exterior wall and ceiling surfaces. Ideal for textured substrates, glass fabrics as well as textured and embossed wallpapers.

Preparation

For all mineral substrates (such as concrete, masonry, levelling compounds, cement, gypsum and lime plaster), plasterboard and other drywall, firmly adhering emulsion paint coats as well as woodchip, glass fabric and other paintable wallpaper and wall coverings. The substrate must be dry, clean, stable, absorbent and free of dust and grease. Remove loose material, old wallpaper and poorly adhering paints from the substrate. Prime highly absorbent, sanding and chalking substrates with baufan Deep Primer LF. Repair cracks, holes and unevenness with a suitable baufan levelling compound.

Processing

Stir well before use and apply with a roller, brush, paintbrush, flat brush or suitable spraying equipment. As a primer, the paint can be diluted with max. 5 % water, as a top coat apply undiluted after the first coat of paint has dried. When coating larger areas, work wet-on-wet to avoid build-up. Clean tools with water immediately after use. Drying time: approx. 5 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); longer drying time under unfavourable conditions. Tinting: With a maximum of 10% universal tinting concentrates or full tone and tinting paint. Notes on airless spray application: Spray angle: 50° Nozzle: 0.023 - 0.027 Spray pressure: 120 - 180 bar

Consumption

Smooth surfaces/fine plaster grain → from 150 ml/m² Determine exact consumption quantity by test coating on the object.

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least until: see batch label.

Notes

Application temperature : +5 °C to +30 °C for material, ambient air and substrate Do not cover surfaces to be painted. Keep out of reach of children. Ensure adequate ventilation during application and drying. Do not inhale spray mist. Avoid eating, drinking and smoking while using the paint. Wear safety goggles. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Only dispose of empty containers for recycling. Hazardous respirable droplets may be produced when spraying. Do not inhale aerosol or mist. Use combination filter A2/P2 when spraying.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.