

Deeply Penetrating Primer - solvent-free

Technical information sheet

1l / Item no.101506 / EAN 4016215101506
5l / Item no.101520 / EAN 4016215101520
10l / Item no.101551 / EAN 4016215101551



Our special primer with a high penetration effect penetrates deep into the substrate, reliably consolidates sanding and chalking surfaces and ensures even, reduced absorbency. The ideal basis for long-lasting coatings and perfect end results - safe, efficient and professional.

- Solvent-free Hydrosol acrylate primer
- High depth effect due to ultra-fine hydrosol dispersion
- Ready-to-use for consolidating sanding and chalking substrates
- Can be diluted up to 1:1 with water to regulate absorbency
- transparent drying
- for indoors and outdoors

Area of application

baufan Tiefgrund LF is a special primer with a high penetration depth for consolidating sanding and chalking substrates and for reducing absorbency.

Preparation

Suitable for all mineral substrates such as concrete, plaster, brick, etc. and for plasterboard. The substrate must be clean, dry, absorbent and free of release agents. Substrates that cannot be consolidated or do not adhere sufficiently must be completely removed. If in doubt, create a test surface.

Processing

Coordinate the primer with the subsequent product. To regulate the absorbency, baufan Tiefgrund LF can be diluted with water up to 1:1. Shake or stir well before use and apply with a brush, paintbrush or suitable spraying equipment. Clean tools with water immediately after use. Cover surfaces not to be treated beforehand, as dried splashes are difficult to remove later. Drying time: approx. 6 - 8 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); longer drying time under unfavourable conditions.

Consumption

1 litre = approx. 10 m² for undiluted coating Determine the exact consumption quantity by applying a test coat to the object.

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least 24 months from date of manufacture (see batch label).

Notes

Processing temperature: +5 °C to +30 °C for material, ambient air and substrate Keep out of reach of children. Ensure adequate ventilation during application and drying. Do not inhale spray mist. Avoid eating, drinking and smoking while using the paint. Wear safety goggles. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Only dispose of empty containers for recycling.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.