

2,5kg / Item no.007302001 / EAN 4007955073024

700g / Item no.007301001 / EAN 4007955073017



Solvent-free contact adhesive for the secure bonding of cork in floor areas as well as Styrofoam®, wooden skirting boards, carpets and similar materials. Also adheres reliably to non-absorbent substrates and enables clean, durable application indoors.

- Ideal for laying carpet on steps
- Very low emission according to EC 1 plus
- immediately accessible
- Suitable for chair castors according to DIN EN 12529
- Suitable for underfloor heating
- Styropor® - registered trademark of BASF SE

Area of application

Universeller Kontakklebstoff mit hoher Festigkeit für Teppich, Kork, Styropor® und Holzleisten auf Holz, Stein und Metall.

Preparation

Mineral substrates, V100 chipboard, OSB boards, wood, parquet, laminate, linoleum, metal and similar substrates are suitable. The substrate must be dry, sound, clean and even. Remove wax, grease, dirt, dust and other contaminants. Prime highly absorbent, sanding and chalking substrates - e.g. with Tiefengrund LF or Putz- und Haftgrund. Level rough and uneven floor surfaces with floor levelling compound. The coverings to be bonded must be conditioned, relaxed and levelled.

Processing

Apply contact adhesive to both sides of the substrate and the material to be bonded using a short-pile roller or brush to create a closed film. Allow the contact adhesive to flash off until it has dried transparently (approx. 30 - 90 minutes depending on the covering and substrate). Then lay the covering in the correct position and press down firmly, first in the seam area and then over the entire surface. It is essential that the flooring is laid accurately, as it is no longer possible to correct it once the two layers of adhesive have come into contact. Work on large areas in sections, as the flooring can be laid for a maximum of 2 hours after the adhesive has dried transparently. The bonded floor coverings can be walked on immediately and are fully load-bearing after one day. Surface treatment after 24 hours at the earliest.

Consumption

Approx. 250 g/m² for double-sided application

Storage

Keep container tightly closed and store in a cool but frost-free place. Keep out of the reach of children.

Notes

Not suitable for bonding PVC. The installation guidelines of the flooring manufacturer must be observed. Do not use below +15 °C object and room temperature or above 75 % humidity. Remove adhesive residues immediately with water. Clean tools with water immediately after use. Dried material residues can be disposed of with household waste or construction site waste. Dispose of uncured residues according to EWC waste code no. 08 04 10.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.