



Linseed Oil Putty

Technical information sheet

500g / Item no.520810 / EAN 4016818390666

1kg / Item no.520812 / EAN 4016818390673



High-quality window putty for durable glazing and repairs. Easy to apply and provides a weather-resistant seal for glass panes in wooden and metal frames.

- according to DIN 18545
- Proven quality
- Colour beige

Area of application

Glazing putty made from natural raw materials for single and repair glazing on wooden windows with exposed sealant bevel.

Preparation

The window frame must be clean, dry and free of grease. The rebates must be primed (with acrylic paint or an alkyd resin primer). However, to ensure optimum adhesion of the glazing putty, the primer must not be applied so thickly that it blocks the pores of the wood.

Processing

After kneading, press the glass putty firmly into the rebate and smooth the surface with a putty knife. During the drying time, it is essential to prevent any condensation from penetrating the putty bed. As the putty requires oxygen to set, double windows must not be assembled immediately after glazing. After curing, after 4 - 8 weeks at the latest, the putty must be painted over with weather-resistant elastic paint. Painting over too early can lead to wrinkling. Preliminary tests should always be carried out on acrylic paints. The provisions of the BFS guideline, DIN 18361 and DIN 18545 must be observed.

Consumption

500 g for approx. 50 - 60 cm

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, it will keep for at least 24 months from the date of manufacture (see label).

Notes

Processing temperature: at least + 8 °C for material and circulating air Keep out of reach of children. Do not allow to enter the sewage system, waterways or soil. Only dispose of empty containers for recycling.

Status: 15.08.2026

Page 1/1

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Phone +49 (0)341 44655-0 ■ E-mail info@baufan.de ■ Internet www.baufan.com

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.