



Synthetic resin-reinforced wallpaper paste with extra high adhesive strength for heavy wallpapers. It is ready to use in just 30 minutes, can be applied by machine and is free from preservatives. Ensures even adhesion without bubbles.

- Reinforced with synthetic resin
- Extra high adhesive strength for heavy wallpapers
- Ready to use in 30 minutes
- machinable
- free from preservatives

Area of application

Cell glue for gluing heavy wallpaper.

Preparation

The substrate must be clean, dry, sound and free of separating agents (dust, grease, etc.). Remove old wallpaper with baufan wallpaper stripper or baufan woodchip stripper. Repair cracks, holes and uneven surfaces with baufan interior filler. Prime sanding and chalking substrates with baufan Deep Primer LF. Pre-paste highly absorbent substrates (1:40 ratio) or pre-treat with baufan Deep Penetrating Primer LF.

Processing

Mixing ratio: Pre-pasting: Mix 1:40 = 8.0 litres of water = 60-80 m² Heavy wallpapers: Mix 1:20 = 4.0 litres of water = 20-25 m² Sprinkle the contents of the pack quickly and rapidly into cold water while stirring vigorously and continue stirring for a short time. After approx. 30 minutes, stir the mixture again vigorously. Coat the wallpaper evenly, fold and leave to soak. After the recommended soaking time, apply the wallpaper butt-jointed and press it down evenly and bubble-free.

Storage

Store in a childproof, cool and dry place.

Notes

Always follow the wallpaper manufacturer's instructions for use. Free from preservatives, so the mixed paste should be applied soon. Remove any paste residue on the front of the wallpaper immediately with a damp cloth. Do not process below +5 °C object and room temperature. To further increase the adhesive strength and for slightly absorbent substrates, we recommend adding 20 % baufan wallcovering adhesive, which is stirred into the ready-mixed cell glue. Material residues can be disposed of with household waste or as construction site waste. EWC waste code no. 08 04 10.

Note:

All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.