Lining Paper

Technical information sheet

1kg / Item number 102107 / EAN 4016215102107



For optimum substrate preparation before wallpapering. The cellular maculate smoothes rough and uneven plasters, reliably fills pores and equalises different absorbencies. This ensures that the wallpaper adheres evenly and makes wallpapering much easier. Ideal for preparing wall surfaces for a clean, even and professional wallpapering result indoors.

- Substrate pre-treatment before wallpapering
- For smoothing rough and coarse-pored plaster surfaces
- regulates the absorbency
- for brush and trowel application
- Water vapour permeable and breathable
- free from preservatives

Area of application

Cellular maculate as a paintable and trowelable wallpaper base for rough plaster. Smoothes, fills pores, regulates absorbency and improves adhesion.

Preparation

All substrates must be clean, dry, sound, absorbent and free of release agents. Use baufan Deep Penetrating Primer LF to increase the strength. Substrates that cannot be consolidated or do not adhere sufficiently must be completely removed. Repair cracks, holes and break-outs with baufan interior filler. If in doubt, carry out a test application.

Processing

Stir the contents of the pack into the appropriate amount of clean, cold water. Mixing ratio: Mix 1 kg of baufan cellular maculate with approx. 6 litres of water. After a swelling time of approx. 30 minutes, the spreadability can be optimised by adding more. It can be applied with a roller, brush, paintbrush or flat brush. If baufan Zell-Makulatur is to be levelled, e.g. to level coarse plaster, reduce the amount of water accordingly. (1 kg powder to 4 - 5 litres of water). Clean tools with water immediately after use. As baufan Zell-Makulatur does not contain any preservative, the mixed product must be used promptly. Drying time: approx. 24 hours under normal conditions (+20 °C, 65% relative humidity, moderately absorbent substrate); in unfavourable conditions, the drying time is correspondingly longer.

Consumption

1 kg is sufficient for approx. 20 - 25 m² - depending on the application method and substrate condition Determine the exact amount used by trial application on the object.

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least 48 months from date of manufacture (see batch label).

Notes

Application temperature: +5 °C to +30 °C for material, circulating air and substrate Do not cover surfaces to be painted. Keep out of reach of children. Ensure adequate ventilation during application and drying. Avoid eating, drinking and smoking while using the paint. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not allow to enter drains, waterways or soil. Only dispose of empty containers for recycling. Product code M-DF01

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.