Wallpaper Paste

Technical information sheet

200g / Item no.102206 / EAN 4016215102206
4kg / Item no.102268 / EAN 4016215102268

High-quality Zell paste for hanging light and standard weight wallpapers. The wallpaper paste mixes smoothly without lumps and is ready for use after 30 minutes. It can be applied using either a pasting machine or a paste brush.

- Cell glue
- High adhesive strength
- does not clump
- Ready to use in 30 minutes
- machinable
- free from preservatives

Area of application

Cellulose paste for light and standard wallpapers.

Preparation

The substrate must be sound, dry, uniformly absorbent, smooth and clean. Remove any old paint and wallpaper. Fill cracks, holes and uneven areas with a suitable baufan filler. Consolidate sandy and chalky substrates with baufan Tiefgrund LF. Apply a base coat to highly absorbent substrates or prime them as well. Apply a primer coat of baufan Zell-Makulatur to coarse-grained plaster.

Processing

For standard paper wallpaper, gradually sprinkle 200 g of baufan wallpaper paste into 5 l of cold, clean water whilst stirring vigorously, and continue stirring for a short while. For hanging heavy wallpaper, use 4 litres of water for 200 g of wallpaper paste. After 30 minutes, stir the mixture vigorously once more. Once the soaking time has elapsed, further dilution is possible depending on the quality of the wallpaper. Apply the wallpaper paste evenly to the back of the wallpaper using a pasting machine or a brush, fold the strip of wallpaper and hang it after allowing the prescribed soaking time in accordance with the manufacturer’s instructions. Remove any residue of wallpaper paste with a damp cloth. Clean tools with clean water after use.

For wallpapering on primed surfaces, add 20% baufan latex binder to the fully mixed wallpaper paste (750 g latex binder per 200 g batch of wallpaper paste). Adding 20% baufan latex binder is also recommended to increase moisture resistance and when working on critical substrates (e.g. fresh cement render).

Consumption

Approx. 200 ml of the prepared wallpaper paste per m² – depending on the surface.

Storage

Store containers tightly sealed and in a dry place.

Notes

Application temperature:
at least +5 °C for the material, ambient air and substrate

The wallpaper manufacturer’s application instructions must be followed at all times.

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

Keep out of the reach of children. In case of contact with the eyes, rinse immediately and thoroughly with water. Do not allow the product to enter the mains drainage system, watercourses or the ground.

Please refer to the safety data sheet for safety-related information. Up-to-date safety data sheets are available on our website at www.baufan.de.

Disposal:
Only send completely empty containers for recycling. Dried-out material residues can be disposed of as household waste or as construction site waste. EWC waste code no. 08 04 14.

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.