Waterproof Wood Glue D3

Technical information sheet

500g / Item number 102466 / EAN 4016215102466
1kg / Item number 102473 / EAN 4016215102473



Waterproof wood glue in accordance with DIN EN 204-D3 for high-strength and durable gluing indoors and outdoors. Suitable for all types of wood, wood-based panels, OSB and laminate. The glue is solvent-free, dries transparently and forms an elastic, age-resistant joint. Ideal for furniture construction, assembly work, dowel and tenon joints as well as tongue and groove gluing with high load-bearing capacity.

- for waterproof gluing in accordance with DIN EN 204-D3
- Ideal for all types of wood, OSB boards and laminate
- solvent-free
- dries transparent
- tested by ift Rosenheim - Expert opinion no. 11-002804-PR01 (PB GAS-K01-11-en-01) dated 23/09/2011
- for indoors and outdoors

Area of application

baufan Wood Glue D3 is suitable for gluing all commercially available types of wood, wood-based materials and laminates.

Preparation

Prepare the workpieces to be glued properly. The gluing surfaces must be clean and free of grease and dust. The ideal wood moisture content is 8-12 %. Higher humidity prolongs the setting time.

Processing

Apply baufan wood glue D3 on both sides with a brush or glue comb. The total application quantity should be 150 - 200 g/m². After the shortest possible flash-off time, press the parts to be joined together while still damp. The pressing pressure should be approx. 1 N/mm² and should be maintained for approx. 15 minutes. For laminate boards, the pressing pressure can be increased to 3 N/mm² and the pressing time to 30 minutes. When laying pre-finished parquet or laminate flooring, apply baufan Wood Glue D3 in strands on both sides of the tongue, push the flooring elements together and tap them together. Immediately wipe away any excess glue with a damp cloth. Always observe the adhesive guidelines of the flooring manufacturer. Clean tools with water immediately after use.

Consumption

depending on the substrate ► from 150 - 200 g/m²

Storage

Keep container tightly closed in a cool but frost-free place. If unopened and stored properly, shelf life is at least until: see batch label.

Notes

Processing temperature: at least + 5 °C for material and circulating air The drying time depends on the processing temperature. Relative humidity above 90%, especially in conjunction with low temperatures, can significantly affect the drying time and quality properties. GISBAU - GISCODE for installation materials: D1 Waste code no. 080410. Only empty containers should be sent for recycling. Dried material residues can be disposed of according to waste code no. 080410 (waste adhesives and sealants with the exception of those falling under 080409) or 170904 (mixed construction and demolition waste with the exception of those falling under 170901, 170902 and 170903) or as household waste.

Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

Note:
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.